



TEST REPORT

Date: 6/10/2008

TEST NUMBER: 114603

CLIENT	Dyerich Flooring Designs, Ltd./Terra Legno
--------	--

TEST METHOD CONDUCTED	ASTM D2394 Falling Ball Indentation Test
-----------------------	--

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	PEBCNT Brazilian Cherry
COLOR	-----
ROLL	-----
CONSTRUCTION	Engineered Wood
FIBER	-----
BACKING	-----
REFERENCE	

PURPOSE

Measure the resistance of a finish flooring to impacts from dropped objects.

PROCEDURE

A ball 2 inch (51 mm) in diameter weighing 1.18 lbs (535 grams) is dropped in a vertical line from a height of 6 inches (152 mm) and progress in 6 inch (152 mm) increments to 6 ft (1.8 m).


The depth of each indentation is measured after each drop by placing the center of the indentation measuring device over the center of the impact area.

TEST RESULTS

Indentation resistance index at a height of drop of 72 inches (1.8 m) = 0.020 inches.

DROP (inches)	DEPTH (inches)
12 inches	0.006 Inch
24 inches	0.012 Inch
36 inches	0.013 Inch
48 inches	0.016 Inch
60 inches	0.019 Inch
72 inches	0.020 Inch

NOTE: No fracture of surface or interior material observed.

APPROVED BY: 

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.